

## 1 Introduction

This classification report defines the classification assigned to « **JET TEX EASY** » (as described by the sponsor) in accordance with the procedure given in EN 13501-1: 2018

### **CLASSIFICATION REPORT OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1: 2007 + A1:2009**

**Sponsor:** **DICKSON COATINGS**  
**415 Avenue de Savoie**  
**38110 Saint Clair de la Tour**  
**FRANCE**

**Prepared by :** **IFTH**  
**Avenue Guy de Collongue**  
**69134 ECULLY CEDEX – FRANCE**

**Notified laboratory N° :** **0072**

**Name of product:** **JET TEX EASY**

**Classification report N° :** **N° 19-01967/1 L**

**Issue number :** **1**

**Date of issue :** **July 23<sup>th</sup>, 2019**

This classification report consists of four pages and may only be used or reproduced in its entirety.

Ce rapport de classement atteste uniquement des caractéristiques de l'échantillon soumis aux essais et ne préjuge pas des caractéristiques de produits similaires. Il ne constitue donc pas une certification de produits au sens de l'article L.115-27 du code de la consommation et de la loi du 3 juin 1994.

## 2 Details of classified product:

### 2.1 General:

Product « **JET TEX EASY** » (as described by the sponsor) is defined as stretched ceilings in accordance with EN 14716: 2004.

### 2.2 Description of the product:

Product « **JET TEX EASY** » (as described by the sponsor), is described below or in the test report provided in support of classification listed in 3.1 :

Fabric made of 100% polyester with inherent flame retardant acrylic and polyurethane coating on both sides.

Nominal surface weight: 280 g/m<sup>2</sup> ± 10%

Nominal thickness: 0,3 mm ± 10%

Colour: White (front side) / Grey (back side)

## 3 This reports and results in support of classification:

### 3.1 Reports:

Name of Laboratory	Name of Sponsor	Test report N°	Test method
IFTH Avenue Guy de Collongue 69134 ECULLY Cedex FRANCE	DICKSON COATINGS 415 Avenue de Savoie 38110 Saint Clair de la Tour FRANCE	N° 19-01967 <sup>E1-V1</sup> dated July 23 <sup>th</sup> , 2019	NF EN ISO 11925-2:2013 NF EN 13823: 2013

**3.2 Test results :**

Test method	Parameter	Nb. of Tests	Results	
			Continuous parameter mean	Compliance parameter
EN ISO 11925-2 Applied on the face Time exposure 30s  Burning droplets or particles FRONT SIDE	$F_s \leq 150\text{mm}$ in 60s	6	/	IN ACCORDANCE
	Ignition of paper		/	NO
EN ISO 11925-2 Applied on the face Time exposure 30s  Burning droplets or particles BACK SIDE	$F_s \leq 150\text{mm}$ in 60s	6	/	IN ACCORDANCE
	Ignition of paper		/	NO
EN 13823*	FIGRA <sub>0.2MJ</sub> (w/s) FIGRA <sub>0.4MJ</sub> (w/s) THR <sub>600</sub> (MJ) LFS	3	0 0 0,27 /	/ / / NO REACH
	SMOGRA (m <sup>2</sup> /s <sup>2</sup> ) TPS <sub>600s</sub> (m <sup>2</sup> )		24,13 44,33	/ /
	LDP <sub>f&lt;10s</sub> LDP <sub>f&gt;10s</sub>		/ /	NO NO

\*Specimen fixed on metallic frame with ventilated cavity 80 mm in width behind the sample according to the chapter 4.1.1.3-b of the standard EN 14716: 2004, sides the most remote from the angle and the spaces situated behind every wing being left opened.

**4 Classification and field of application :**

**4.1 Reference of classification:**

This classification has been carried out in accordance with EN 13501-1: 2018

**4.2 Classification :**

Product « **JET TEX EASY** », in relation to fire behaviour is classified: **B**

The additional classification in relation to smoke product is: **s 1**

The additional classification in relation to flaming droplets / particles is: **d 0**

The format of the reaction to fire classification for construction products excluding flooring is:

Fire Behaviour		Smoke Production		Flaming Droplets
<b>B</b>	-	<b>s</b>	<b>1</b>	- <b>d</b> <b>0</b>

**REACTION TO FIRE CLASSIFICATION : B- s1- d0**

**4-3 Field of application :**

This classification is valid for the following product parameters :



Composition: Fabric made of 100% polyester with inherent flame retardant acrylic and polyurethane coating on both sides.  
 Nominal surface weight: 280 g/m<sup>2</sup> ± 10%  
 Nominal thickness: 0,3 mm ± 10%  
 Colors: White (front side) / Grey (back side)

This classification is valid for the following end used application: Stretched ceilings fixed with gap-air, the white side facing the floor.

**5 Limitation :**

This classification document does not represent type approval or certification of the product.

The test laboratory has played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.

Report	Signatory	Signature*	Date
Edited by:	Léa MONIN Ingénieur Tests and Trials		July 23 <sup>th</sup> ,2019
Approved by:	Jean-Marc ORAISON In charge of Fire Regulation for Construction Products		July 23 <sup>th</sup> ,2019

\* For and in the name of **I.F.T.H.**